

Release Coat PW5130

Food-Safe Release Agent

Description

Release Coat PW5130 is a semi-permanent methylphenylpolysiloxane silicone release agent.

Applications

Release Coat PW5130 is a formulated non-stick coating which imparts a hard gloss finish to metal surfaces. It is safe to use with food products and facilitates the easy separation of baked goods from industrial bread pans and cake tins.



Product Features

Release Coat PW5130 is fast curing and semi-permanent formulation which meets US FDA, German BfR and EU criteria for food contact. The life of the coating will be dependent upon factors such as the baking mix, sugar content, amount of release oil used etc.



Product Safety

A Safety Data Sheet compliant with EU 2015/830 is available for Release Coat PW5130 on request. It contains any safe handling guidelines that may be relevant to this product.

Storage, Shelf Life & Packaging

Release Coat PW5130 has a shelf life of 8 months when stored in original and unopened containers between 5°C and 30°C. It is available in 25kg packs.

Compliance

- FDA CFR 21 175.300 (Resinous and Polymeric Coatings)
- German BfR Chapter XV (Silicones)

Typical Properties

Appearance:Dark straw coloured liquidSolids:26.0 - 30.0 %

Please note; these are typical properties only and should NOT be construed or used as a specification for this product.

(OPM3/D3)	TDS: 077	Issue: 01	Revised: 01/05/2019



This product is manufactured in a facility whose Quality Management System is certified as being in Conformity with ISO 9001:2015.



This product is manufactured in a facility which operates in line with the Chemical Business Association's Responsible Care Program.

Technical Support Contact Details

PennWhite Ltd. Aston Way, Midpoint 18 Business Park, Middlewich, Cheshire, CW10, 0HS. Telephone: + 44 (0) 1606 734820, Fax: +44 (0) 1606 837867 Email: info@pennwhite.co.uk. Website: www.pennwhite.co.uk

nation given in this document is based upon technical data gained in our own and other laboratories and is believed to be true. However if the material is used conditions beyond our control we can assume no liability for results obtained or damages incurred through the goplications of the data present herein.



Method of Use

Any metal surface to be coated with Release Coat PW5130 should be clean and free from grease and moisture. When re-coating surfaces remove the old coating by soaking for 24 hours in hot caustic solution.

Release Coat PW5130 should be used as received and no further dilution is required. It can be applied by either dipping or spraying. In most operations a coating thickness of between 10-15 microns will give optimum results. Precise coating depth should be determined by trial. A typical curing cycle for coated articles would be; fume off solvent, Begin with 20 minutes in an oven rising from ambient to 200°C, then 20 minutes at 235°C, finishing with 10 minutes at 250°C.